

UNI-TAPE

抗裂增強彈性防水膠帶

Technical Data & Application Instructions

技術資料

使用說明



產品描述

UNI-TAPE 是由特殊軟性材料和不織布開發而成的多功能膠帶。具有防水、韌性強、耐候和追從裂縫，會隨著裂縫不斷延伸。可以簡單克服屋頂裂縫、防止漏水，為防水抓漏專用材料，節省裂縫修補的時間。

表面處理

1. 素地脆弱部份、塵埃、油份、污物等先予清除。
2. 坑洞部分可先用樹脂砂漿補強。

使用說明

將 UNI-TAPE 裁剪成需要的長度，以乾手撕開貼布的透明膠後，直接貼在施作面上，再用壓貼工具緊密壓貼。馬上會有很好黏著度，24小時之後將達到最大黏度。施做前特別注意表面要乾淨，乾燥以達到最高效能。

產品物性

Tensile Strength(抗張強度)-----	900 psi (±50) [ASTM D2370]
Elongation(伸長率)-----	1000% (±50) [ASTM D2370]
Peel Strength(抗撕強度)-----	9 lbs. per lineal inch (±2) [ASTM D903]
Low Temp. Flexibility(低溫撓性)-----	Passes 180° bend over ½" mandrel at -30°F (-35°C) [Federal Test Method No. 141 a-6221]
Permeance(透氣率)-----	0.001 perms maximum
Tear Strength(撕裂強度)-----	150 pli (±25) [ASTM E96]
Temp Limits for Service(使用溫度限制)-----	-30°F to 180°F (-35°C to 82°C)

包裝

5cm X 15M /12捲/箱 10cm X 15M /6捲/箱

使用限制

溫度於32°F (0°C) 或高於 110°F (43°C)請勿使用。

UNITED COATINGS
LONGEVITY BY DESIGN®
19011 E. Cataldo Ave. • Spokane Valley, WA 99016
(509) 926-7143 • Fax: (509) 928-1116
(800) 541-4383 • www.unitedcoatings.com

NATIONAL ROOFING CONTRACTORS ASSOCIATION ASSOCIATE

RCI

Energy STAR
ASK ABOUT ENERGY STAR

Our products are guaranteed to meet established quality control standards. Information contained in our technical data is based on laboratory and field testing, but is subject to change without prior notice. No guarantees of accuracy are given or implied, nor does UNITED assume any responsibility for coverage, performance or injuries resulting from storage, handling or use of our products. Liability, if any, is limited to product replacement or, if applicable, to the terms stated within the executed project warranty.

UNITED COATINGS
January, 2005
(Supersedes January, 2001)

7 BUTYL-BACKED POLYESTER REINFORCING TAPE
Technical Data & Application Instructions